

# SLIPTTEST AUSTRALIA PTY LTD ~ ABN 80 111 154 324

12 Blackburn Court ELANORA QLD 4221 PH 0418 75 3311

**SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS AS 4586 (2013) "Appendix A" (Wet Pendulum Method)**

Report Prepared For: **DISTINCTIVE TILE IMPORTS (DTI)** Client Address: **485 ZILLMERE ROAD ZILLMERE QLD 4034**

Property Tested: **VITRA 30 x 30 885271 Dotti Tobacco Mercato VH36** Test Report No: **KO010216-10** Issue Date: **01.02.16**

**Testing was carried out using the Wet Test Method, using Slider 96 (4S) rubber slider, in accordance with Australian Standard AS 4586 Appendix A**  
**Slider was conditioned/prepared using P400 abrasive paper and 3 µm lapping film**

Number of sites tested	5	Test Surface No.	Surface Type	Surface Gradient Degrees	Type and extent of Cleaning Performed	Results of last three swings British Pendulum Number			Slope Correction value (SCV)	Classification of Pedestrian surface materials according to the AS 4586 wet pendulum test	Comments
						Mean BPN Test	Slope Correction value (SCV)	Results of last three swings British Pendulum Number			
Tile 1		1		<1.5	Water & Scrubbing	41	41	41	N/A		
Tile 2		2		<1.5	Water & Scrubbing	40	40	40	N/A		
Tile 3		3	TILE	<1.5	Water & Scrubbing	41	41	41	N/A	<b>P3</b>	
Tile 4		4		<1.5	Water & Scrubbing	40	40	40	N/A		
Tile 5		5		<1.5	Water & Scrubbing	40	40	40	N/A		

**Temperature:** 33 °C **Indoors** **Mean BPN Slip Resistance Value (SRV)** **40** **The above classification is provided without Slope Correction Values**

Testing Instrument: Munro Portable Skid Tester # 1133 Calibration Date: 24.08.15 **Sliptest Australia Pty Ltd**

Testing Officer & Signatory: **KATHRYN ORDING**  **Materials Testing Laboratory - Accreditation number 15374**

Fixed Test: Testing is performed in the anticipated direction of pedestrian travel **12 Blackburn Court ELANORA QLD 4221**

**Unfixed Test :** Testing is performed in the direction of least anticipated slip resistance **Accredited for compliance with ISO/IEC 17025. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/National standards.**

Notes:

